

## CLAIMS

1. An absorbent resin particle comprising:  
a crosslinked polymer (A) including, as essential constituent units, a  
water-soluble vinyl monomer (a1), and/or a vinyl monomer (a2) that is formed  
5 into the water-soluble vinyl monomer (a1) by hydrolysis, and an internal  
crosslinking agent (b); and  
a hydrophobic substance (C),  
wherein  
the absorbent resin particle has a structure such that a part or an  
10 entirety of the hydrophobic substance (C) is contained in the inside of each  
particle of the absorbent resin particle.
2. The absorbent resin particle according to claim 1, wherein  
the structure such that a part or an entirety of the hydrophobic  
15 substance (C) is contained in the inside of each particle of the absorbent resin  
particle is a structure such that each particle of the absorbent resin particle  
contains a connection (RC) formed with the hydrophobic substance (C).
3. The absorbent resin particle according to claim 1, wherein  
20 the structure such that a part or an entirety of the hydrophobic  
substance (C) is contained in the inside of each particle of the absorbent resin  
particle is a structure such that a material (D) obtained by coating or  
impregnating a part or an entirety of either a hydrophilic material (d1) or a  
hydrophobic material (d2) with the hydrophobic substance (C) is contained in  
25 the inside of each particle of the absorbent resin particle.
4. The absorbent resin particle according to claim 1, wherein  
the hydrophobic substance (C) has a HLB value in a range of 1 to 10.
- 30 5. The absorbent resin particle according to claim 1, wherein

the hydrophobic substance (C) is a silicone or a modified silicone.

6. The absorbent resin particle according to claim 1, further comprising a diffusing-penetrating agent (E) as a constituent component.

5

7. The absorbent resin particle according to claim 1, wherein the absorbent resin particle exhibits a diffusion absorption amount in a range of 40 ml to 70 ml.

10 8. The absorbent resin particle according to claim 1, wherein the absorbent resin particle exhibits an absorption time (Z) in a range of 0.5 minute to 3.5 minutes, the absorption time being a time necessary for the absorbent resin particle to swell to 70 percent by volume with respect to a saturated swelling degree by absorbing physiological saline.

15

9. The absorbent resin particle according to claim 1, wherein the absorbent resin particle satisfies formulae (2) and (3):

$$30 \leq (X) \leq 70 \quad (2)$$

20  $(Z) \leq -0.0071(Y) + 2.7 \quad (3)$

where

(X) represents a water-retention amount (g/g) of the absorbent resin particle that had been immersed in physiological saline for one hour,

25 (Y) represents a liquid permeation rate (ml/min) under loading of 21.4 Pa at which physiological saline permeates the absorbent resin particle that has been immersed in physiological saline for one hour, and

(Z) represents an absorption time (min) necessary for a sample to swell to 70 percent by volume with respect to a saturated swelling degree by  
30 absorbing physiological saline.

10. The absorbent resin particle according to claim 9, wherein  
the absorbent resin particle further satisfies formula (4):  
$$10 \leq (Y) \leq 100 \quad (4)$$
- 5
11. An absorber comprising:  
the absorbent resin particle according to claim 1; and  
a fibrous material.
- 10 12. An absorbent article comprising an absorber according to claim 11.